

**A-ESSE s.p.a.****FABBRICA OSSIDI di ZINCO**Via Conturri, 33 – 18042 CARASCO (GE) ITALIA – telef. 0185 350177 – 0185 350178 – fax 0185 350863
www.a-esse.com – e-mail: info@a-esse.comCERTIQUALITY
È MEMBRO DELLA
FEDERAZIONE CISO

ANALYTICAL DATA – ZINC OXIDE GOLD SEAL	Ver. EN
---	----------------

Parameters	Unit	Value	Tolerance	Test Method
<i>ZnO content</i>	%	99,9	min.	IL 005
<i>45 µ Sieve Reject</i>	%	Absent		IL 004
<i>250 µ Sieve Reject</i>	%	Absent		IL 004
<i>Surface area (BET)</i>	m ² /g	6	± 1	IL 007
<i>Bulk density</i>	g/cm ³	0.65	± 0.1	IL 002
<i>Loss at 825°C</i>	%	0,25	max.	IL 003
<i>Moisture</i>	%	0,10	max.	IL 006
<i>Cloridric Acid Insolubles</i>		Absent		IL 008
<i>Impurities:</i>				
<i>Pb (PbO)</i>	ppm	50	max.	IL 011
<i>Fe</i>		Traces		IL 011
<i>Cd</i>		Traces		IL 011
<i>Al</i>		Absent		IL 011
<i>Ni</i>		Absent		IL 011
<i>Mn</i>		Absent		IL 011

3	05/09/2018		
REV.	DATA	VERIFICATO	APPROVATO